

ADVANCED PROTECTIVE COATING SYSTEM

VSC™ 1200 TOPCOAT

with
Eastman TETRASHIELD™
protective resin systems

VSC™ 1200 TOPCOAT (Parts A & B)

VSC 1200 Topcoat is a two part (4:1) solvent based topcoat that is a hard, tough and extremely durable heavy duty industrial maintenance coating. The key is in the resin and Eastman Tetrashield™ protective resin systems create coatings that protect. Eastman has a long history of developing innovative polymers to solve the toughest problems and this latest innovation of Tetrashield continues this legacy. Valentus Specialty Chemicals and Eastman have invested thousands of research hours over the past four years to bring this remarkable technology to market.

PHYSICAL PROPERTIES (Mixed)

| | |
|------------------------|--|
| STANDARD COLORS | Gray, White, Black & ANSI Safety Colors |
| CUSTOM COLORS | Available upon request |
| FINISH | High Gloss |
| TACK FREE TIME | 3-3 ½ hours |
| %SOLIDS BY WEIGHT | 76 |
| %SOLIDS BY VOLUME | 64 |
| COVERAGE (Theoretical) | 295 sq. ft./gal @3.5 mils DFT, assumes no Loss |
| RECOMMENDED THICKNESS | 3-4 mils dry (4-6 mils wet) |
| VISCOSITY | 75 Ku |
| WORKABLE POT LIFE | 4 hours at 77°F |
| SAG RESISTANCE | 10+ mils |
| RECOAT TIME | 1-5 hours |
| COATING VOC | 2.8# per gl. (340 gms./l.) |
| FLASHPOINT | 80°F |
| FLAMMABILITY CLASS | Flammable IC |

Advantages:

- Exceptional adhesion
- Excellent long term protection when applied over VSC 1100 Primer
- Excellent resistance to acids, bases, organic solvents & hydraulic fluids
- Consistent film build and ease of application
- Cure window that gets assets back in service quicker

PRODUCT DESCRIPTION:

Premium performance high solids, low VOC two component gloss urethane topcoat

RECOMMENDED USES:

For use over properly prepared and primed steel, galvanized, aluminum, and poured concrete walls and flooring. Can be used over most previously primed and top coated substrates with minimal preparation.

Application over aged silicone alkyd systems is not recommended without total removal down to white metal.

Recommended for use on interior & exterior structural steel, steel piping, storage tank exteriors, bridges, metal buildings, railings, conveyors, pumps & motors and other machinery.

Excellent performance in medium to heavy duty protective maintenance applications for most industrial & commercial environments.



PERFORMANCE DATA

Corrosion ASTM B117 Salt Fog Blasted steel

| Film Build VSC1100 | ASTM B117 rating | With VSC1200topcoat (5 mil dry) |
|--------------------|---|---|
| 3.5-5 mil dry | Greater than 1400 hrs. no face blister, no face rust, less than 2mm scribe rust | Greater than 3000 hr. no face blister, no face rust, less than 3 mm scribe rust |

Chemical resistance VSC 1100/1200 at target film build, 7 day ambient cure, 7 day direct contact exposure

| Material | Rating |
|-------------------------|-----------------------|
| Acid (sulfuric) | Excellent – no damage |
| Base (sodium hydroxide) | Excellent – no damage |
| Solvents | Good |
| Brake Fluid | Good (some softening) |
| Hydraulic Fluid | Excellent |
| Water* | Excellent |
| Salt water* | Excellent |

*Not recommended for immersion

Weathering: VSC 1100/1200 at target film build, 7 day ambient cure 60 degree gloss retention

| Method | Rating |
|--------------------------|---------------------------------|
| Xenon ASTM 7869 | 4000 hrs. > 70% gloss retention |
| ASTM G154 cycle 1 (QUVA) | 6000 hrs. > 70% gloss retention |

Adhesion VSC 1100/1200 at target film build, 7 day ambient cure

| Method | Rating |
|---|-----------|
| Condensing Humidity ASTM D2247 at 60°C 7days blasted steel | Excellent |
| Field exposed Blasted steel | Excellent |
| Field exposed moderately prepared surface (Power wash/scraper over old paint) | Excellent |

DIRECTIONS FOR USE

Recommended Primer: VSC 1100 Aluminum Epoxy high solids low VOC primer. Excellent performance as a Direct to Metal topcoat when applied over properly prepared steel.

SURFACE PREPARATION:

Surfaces must be clean, dry, free from oil, grease, hydraulic fluids, silicone contamination, waxes, or any other residue. Use a solvent or commercial cleaner that does not leave a residue per SSPC-SP 1. Remove all mill scale, rust and any loose paint.

Ensure that previously painted surfaces have adequate adhesion, or remove. Smooth, slick surfaces should also be abraded/scuffed to ensure adequate adhesion. Spot prime or prime overall with VSC 1100 aluminum epoxy as required.

For environments which do not permit abrasive blasting, or over previously painted surfaces, hand tool cleaning per SSPC-SP2, power tool cleaning per SSPC-SP3, and/or high pressure water cleaning per SSPC-SP 12/NACE 5 WJ-4 is recommended.

New Steel & Iron: Abrasive blasting is preferred for enhanced performance. Blast to a commercial finish per SSPC-SP 6/NACE 3 to obtain a 1.5-3 mil profile. Prime overall with ZincGard 1000 inorganic zinc primer, followed by VSC 1100 aluminum epoxy as an intermediate coat. Refer to SSPC Guide 12.0 Painting over Zinc Rich Primers.

Galvanized Steel & Aluminum: Remove all surface contamination with solvent or commercial cleaner that does not leave a residue per SSPC-SP 1.

New galvanized should be sweep blasted or etched with a phosphoric acid solution, or coated with 0.5 dry mils of a phosphoric acid pre-treatment, followed by VSC 1100 aluminum epoxy primer. Old galvanized should be cleaned per SSPC-SP1, and lightly abraded per SSPC-SP 2 or SSPC-SP3, and primed with VSC 1100 aluminum epoxy.

Concrete: For new concrete, minimum cure is 28 days at 75 F and 50% RH or the equivalent. Abrasive blast or acid etch slick or glazed concrete, and remove laitance and form oils. Produce medium surface roughness per SSPC-SP13/NACE 6. Surface should be sealed with VSC 1100 aluminum epoxy.

For previously painted concrete, clean surface and remove all loose paint and debris with hand or power tools, and high pressure water cleaning. Spot prime bare concrete or seal overall as necessary with VSC 1100 aluminum epoxy.

APPLICATION:

MIXING: 4 parts VSC 1200 Topcoat Part A

1 part VSC 1200 Topcoat Part B

- Material is supplied in two containers as a unit, always mix a complete unit in the proportions supplied. Once the unit has been mixed, it must be used within the working pot life specified.
- Mix Part A thoroughly with low speed power agitation
- Then combine components, blend 1 Part B into 4 Parts A and thoroughly agitate the mixture with low speed power agitation.
- There is no induction period required, material is ready to use
- Do not apply material beyond the recommended pot life
- Do not mix previously catalyzed material with fresh material
- DO NOT MIX PARTIAL KITS - ONLY USE ONE & FIVE GALLON KITS AS SUPPLIED

METHOD OF APPLICATION: Air, Airless or Air Assisted Airless Spray, Brush or Roller

Brush or Roller: No thinner is necessary throughout the workable pot life window. Use a natural bristle brush or medium nap roller with a solvent resistant fibers & core. Work coating into all gaps and crevices. Apply wet and avoid excessive brushing or re-rolling.

Airless or Air Assisted Airless: No thinner is necessary throughout the workable pot life window. An airless pump equivalent to Graco Bulldog 30:1 ratio at 1900-2100 psi is recommended, with a 60 mesh in line filter. Use .013" to .0315" spray tip. Good results have also been achieved with a Graco 60:1 Bulldog pump at 45 psi, using a 517-519 tip. A Graco air assisted 30:1 pump or equivalent 1900 - 2300 psi, and 65 psi atomizing pressure is recommended, using a 311 reversible tip. **Optimum results have been achieved using a .017" tip at 2600 psi with a 3/8" ID hose and no thinning.**

Conventional Air: A small amount of thinning may be required for good atomization. If necessary, use only VSC 8100 Thinner at 2-3% by volume maximum. Industrial sprayers such as DeVilbiss MBC or JGA and Binks 18 or 62, fitted with a double regulated pressure pot, 3/8" ID minimum material hose and a .070"-.086" ID fluid tip and matching air cap, are recommended.

CLEANUP & PROLONGED WORK STOPPAGES: Do not allow material to remain in hoses at the end of a job, or during prolonged work stoppages.

Thoroughly flush & clean all equipment immediately after use with Acetone or MEK. Any mixed topcoat should not be re-used after its workable pot life.

All excess material and empty containers should be disposed of in accordance with appropriate local, state and federal regulations.

SHELF LIFE: 2 years from date of manufacture unopened at 77°F

CAUTION: For industrial use only. Read and follow all caution statements on this product data sheet, and on the Material Safety Data sheet for VSC 1200 2K Urethane Topcoat

HEALTH & SAFETY: This is a Flammable IC material. Use explosion proof general and local exhaust ventilation. Good general ventilation (typically 10 air changes per hour) should be used.

In confined spaces (or when spraying) use a chemical respirator with organic vapor cartridge and full facepiece.

WARRANTY: Any recommendation by Valentus Specialty Chemicals contained herein, covering the use, utilization, chemical or physical properties and other qualities of our products sold is believed to be reliable, and meet the performance standards as published in our brochures and technical data sheets, when applied and tested under our prescribed conditions; however, Valentus Specialty Chemicals makes no warranty or representation with respect thereto. Use or application is at the discretion of the Buyer without liability or obligation whatsoever of Valentus Specialty Chemicals.

REVISION DATE: September 2017